

## TECHNICAL DATA SHEET



### RITECRETE<sup>®</sup> 2K

Two Component Cementitious  
Elastic Waterproofing Membrane

(Ref. SIPL / TDS / RITECRETE2K / 0421 / R-01)

### ❖ Product Description

**MYMIX - RITECRETE<sup>®</sup> 2K** is two components, polymer modified, highly flexible cementitious water proofing membrane system. It comprises of superior quality cement, other additives and liquid polymers. When both liquid and powder mixed together and applied it forms a tough, flexible and seamless waterproof barrier which also provides excellent bonding and crack bridging ability on masonry substrates.

### ❖ Special Features

- Excellent water proofing property
- Highly flexible & excellent adhesion to masonry substrates
- Provide protection against carbonation
- Good crack bridging ability & seamless
- High resistance to chloride & other salts



## ❖ Application

- Suitable for waterproofing of any concrete, Cement or cementitious surfaces
- Waterproofing of showers, bathrooms, toilets and sunken slabs
- Suitable for terraces, concrete roofs and balconies
- Suitable for concrete foundations & concrete walls, parking decks
- Suitable for prefabricated concrete constructions

## ❖ Advantages

- Easy & user friendly application by Brush, roller or trowel
- Excellent crack bridging property
- Creates seamless coating
- Anti-carbonation & Anti-Efflorescence properties
- Excellent adhesion with substrate
- Excellent water proofing properties
- Highly flexible and elastic, thus accommodate thermal movement
- Flexible film can withstand against moderate hydrostatic pressure
- Good elongation at failure (approx. 80%)
- Free from VOC

## ❖ Suitable Substrates

- All cementitious surfaces
- Old and new concrete surfaces
- Cement plaster and any masonry work

## ❖ Consumption

- Approx. 1.74 kg / m<sup>2</sup> per mm of thickness (Brush / Roller / Flat Trowel Application)
- Coverage may vary depending upon the site condition and substrate absorption

## ❖ Packing

**15 KG** (Part A - Liquid Component - 5 kg + Part B - Powder Component - 10 kg)

## ❖ Shelf Life

Factory sealed packs are best before 12 months from the date of manufacturing in unopened condition and stored in cool & dry area

## ❖ How to Apply

### Surface Preparation

- The surface should be clean and free from dirt, oil or grease before application
- Ensure that the substrate is flat, stable, well adhered, and has a normal absorption
- In case of undulations, correct the local undulation/damage on the substrate at least 48 hours before the application.
- To get flat substrate; prepare mortar using **MYMIX SBR 330 / SBR Latex** for better performance.
- Dampen the wall or floor before application. Remove excess water before application
- The proper preparation of the surface will make the application easier & quicker ensuring a better result
- New concrete is recommended to be 1 month old and completely dried before application

### Mixing

- Take 5 kg Liquid (Part A - RITECRETE<sup>®</sup> 2K) in to a clean mixing bowl or bucket and add 10 kg Powder (Part B - RITECRETE<sup>®</sup> 2K)
- Stir properly for 5 minutes by hand or an electric stirrer to get a smooth & homogeneous slurry mixture
- After stirring wait for 5-10 minutes, stir once again
- Ensure that no powder, lumps particle and unmixed material left in the mixture

### Application

- Use the appropriate tools like brush / roller / flat trowel to spread the material uniformly
- Ensure that first coat applied properly to cover all the areas of substrates without any gap.
- Allow first coat to dry completely for approx. 3-4 hrs before application of 2nd coat.
- Apply second coat after First coat is dry to touch, perpendicular to the direction of the first coat.
- The wet film thickness per coat should be between 0.8 mm to 1.00 mm
- Wait for at least 7 days for complete curing after applying MYMIX RITECRETE<sup>®</sup> 2K
- Clean tools and other items immediately after the use





## ❖ Notes on Application / Limitations

- Do not add water, aggregates or any binders during the application
- If mixture is already hardening; do not use water or Part A liquid component to make usable again.
- During waterproofing of terraces, balconies or swimming pools, it is recommended to add alkali fiber - glass mesh to the first layer of RITECRETE<sup>®</sup> 2K.
- Always add powder to liquid and never add liquid to powder
- Product performance on site varies subject to site conditions and installation procedure followed.
- Do not add any other materials or substances like sand, aggregates, cements etc to the product. It may adversely affect the performance of product.
- Protect from rain and water spillages for the first 24 hours after two coats of application.
- Do not Leave RITECRETE<sup>®</sup> 2K exposed in swimming pools and wet areas. It should cover with tile or stone finishes.
- To improve further elongation & crack bridging ability, polypropylene fiber mesh can be used between 2 coats of RITECRETE<sup>®</sup> 2K.

## ❖ Technical Data

### General Properties

Testing Parameters	Result
Physical Appearance	Part-A : Milky white ; Part-B : Grey colored powder
Mixing Ration (Liquid : Powder) by weight	1 : 2 (A:B)
Pot Life	1 Hour
Waiting time before applying 2 <sup>nd</sup> coat	3 - 4 Hours
Cure time after applying 2 <sup>nd</sup> coat	24 Hours
Waiting time before applying tiles / further application	7 DAYS
Application Temperature	8 <sup>o</sup> - 40 <sup>o</sup> C

### Physical Properties

Property	Test Method	Typical Results
Adhesion Strength on concrete after 7 days (N/mm <sup>2</sup> )	ASTM D 4541	1.75 - 2.0
Adhesion Strength on concrete after 7 days Water Immersion (N/mm <sup>2</sup> )	ASTM D 4541	1.00 - 1.2
Film Tensile Strength in (N/mm <sup>2</sup> )	ASTM D 412	2.75 - 3.2
Film Elongation at Break (%)	ASTM D 412	80
Crack bridging (mm)	ASTM C 836	1

## ❖ Standards Followed

- ASTM D 4541
- ASTM D 412
- ASTM C 836

## ❖ Precautions

- Keep out of reach of children
- Wear suitable protective cloths, respirator and gloves
- In case of contact with skin / eyes, wash immediately with plenty of water & seek medical help

Follow us on:

### Disclaimer



is a Registered Trademark of Sanghavi Industries Pvt Ltd.

The information given in this TDS is for general guidance only. Specific instruction for various site conditions can be provided on demand.

The product information & application details given by the company & its agents has been provided in good faith & meant to serve only as a general guideline during usage. Users are advised to carry out tests & take trails to ensure on the suitability of products meeting their requirement prior to full scale usage of our products. Since the correct identification of the problems, qualities of other materials used and on site workmanship are factors beyond our control, there are no expressed or implied guarantee/warranty as to the results obtained. The company does not assume any liability or any consequential damage for unsatisfactory results, arising from the use of our products.