



TECHNICAL DATA SHEET



SEALER 210

(Unique Water Repellent for all Porous Surfaces)

(Ref. SIPL / TDS / SEALER210 / 0622 / R-00)

Product Description

MYMIX - SEALER - 210 is a liquid with specialized formulation (water based) to seal the porosity of all types of concrete surface. MYMIX - Sealer - 210 has unique water repellent properties that acts as invisible barrier and provides resistance to moisture and reduces staining, effect of efflorescence, while allowing vapour to escape.

Special Features

- MYMIX Sealer 210 is a liquid with specialized formulation (water based) to seal the of all types of concrete surfaces
- Unique water repellent properties
- Acts as a mild penetrating sealer
- Preserves the natural looks
- U.V transparent and non-yellowing

BEFORE



AFTER





(Ref. SIPL / TDS / SEALER210 / 0622 / R-00)

❖ Application

- All kind of natural stones, marble, granites, limestone, bricks and concrete products

❖ Advantages

- Acts as a penetrating sealer
- Preserves the natural look
- Ready-mix & easy to use
- UV transparent and no yellowing
- Can be applied on interior and exterior surfaces

❖ Suitable Substrates

- Marbles & Granite
- Sand stone
- Cement grout surface
- Bricks & Lime stone

❖ Coverage

- Approx. **70 to 75 sq. ft.** per litre (Depends on porosity of the surface)
- Coverage may vary depending on trowel notch size, substrate smoothness and absorption

❖ Packing

- Available in **1 Litre, 5 Litre & 20 Litre** (Bigger packing sizes are available on request)

❖ Shelf Life

- Factory sealed packs are best before 12 months from the date of manufacturing in unopened condition and stored in cool & dry area



(Ref. SIPL / TDS / SEALER210 / 0622 / R-00)

❖ How to Apply

- Clean the surface with a dry cloth and start applying the sealer with the help of a dry cotton cloth with strokes in single direction. Covering the surface uniformly
- Allow the surface to touch dry before application of the second coat. The time between two coats should be approx. 15-30 minutes. After the second application allow the surface to dry again naturally
- Clean excess sealer from the concrete surface or stone with the help of a dry cotton cloth. If needed buffing has to be done
- Protect the surface for curing, taking care that no traffic is allowed on the floor are till the prescribed time limit which is 72 hours curing

❖ Notes on Application / Limitations

- Do not use MYMIX Sealer 210, when the surface has wet condition
- Do not use lesser porosity of tile and stone

❖ Technical Data

General Properties

Sr.No.	Testing Parameters	Typical Results
1.	Colour	Clear Liquid
2.	Ph.	8-10
3.	Specific Gravity	1 gm / ml

❖ Precautions

- Keep out of reach of children
- Wear suitable protective cloths, respirator and gloves
- In case of contact with skin/eyes, wash immediately with plenty of water & seek medical help

Disclaimer

Follow us on:



is a Registered Trademark of Sanghavi Industries Pvt Ltd.

The information given in this TDS is for general guidance only. Specific instruction for various site conditions can be provided on demand.

The product information & application details given by the company & its agents has been provided in good faith & meant to serve only as a general guideline during usage. Users are advised to carry out tests & take trails to ensure on the suitability of products meeting their requirement prior to full scale usage of our products. Since the correct identification of the problems, qualities of other materials used and on site workmanship are factors beyond our control, there are no expressed or implied guarantee/warranty as to the results obtained. The company does not assume any liability or any consequential damage for unsatisfactory results, arising from the use of our products.