

TECHNICAL DATA SHEET



AQUAFLEX[®] AWP 350

ADVANCED WATERPROOFING MEMBRANE

(Ref. MBPL / TDS / AWP 350 / 0524)

❖ Product Description

AQUAFLEX[®] AWP 350 is an advanced, one component, elastomeric waterproofing membrane which is thixotropic in nature and has UV resistance properties. It is ideal for use on exterior horizontal surfaces. It has been formulated to create a rigid bond to most surfaces. AQUAFLEX AWP 350 forms a tough, flexible waterproof membrane with a high film strength that will expand and contract under normal substrate movement & climate changes. It is supplied as a thixotropic liquid, which is easily applied to horizontal surfaces. The formulation is fully optimized to ensure quick tack free time, fast cure, high solids and excellent resistance to swelling, durability of coating emphasize privilege of premium quality acrylic emulsion polymer, pigments, graded additives that are durable with weather and UV resistant. Used as a waterproofing and protective coating for interior & exterior application, having excellent resistance to micro-organisms (Algae, Fungi, molds & other) growth.

❖ Special Features

- Excellent thermal expansion & contraction- Elongation (>350%).
- Anti-chalking property.
- Excellent Crack bridging.
- Excellent corrosion & Water resistance
- Superior appearance with smooth finish.
- Negligible porosity product.
- High film thickness builds up.
- Eco-friendly & cost effective, easy to apply.
- Solvent free composition.
- Superior tensile strength.
- Available in White, Teracotta & Grey Colour.



❖ Application

- Balconies & Decks.
- Under tile waterproofing.
- All horizontal and inclined masonry surfaces.
- Terraces & Parapet Walls.
- For Surface Protection.
- Roof Tops.

❖ Advantages

- Eco-friendly, no toxic chemicals & Heavy metals used.
- Excellent long life with antimicrobial properties.
- High heat reflectance which keeps building cool.
- Easy to apply by brush, roller and spray gun.
- Easy to clean with water and soaps.

❖ Suitable Substrates

- Old & New Masonry surfaces.
- Asbestos & Asphalt Sheet.
- Metal Surfaces.
- Wood Substrate (MDF, Particle Board).

❖ Coverage

- 13 - 15 sq. feet / kg for two coats (DFT 450 - 500 Micron)
- Dry Time is 2-3 Hour.
- Above results are as per standard laboratory conditions
- Coverage may vary depending upon the site condition and substrate used.

❖ Packing

- Available in **4, 10 & 20 kg** (Bigger pack size available on demand).

❖ Colour

- Available in White, Teracotta & Grey Colour.

❖ Shelf Life & Storage

- Factory sealed packs are best before 12 months from the date of manufacturing in unopened condition and stored in appropriate container of Rigid PVC, HDPE, finished Stainless steel, ceramic and enamelled/rubberized containers.
- To avoid attack of micro-organisms, appropriate preservatives (APEO Free) added prior to storage/transportation, appropriate preservative chosen based on system compatibility and efficiency of preservative.

❖ How to Apply

Surface Preparation

- The surface should be clean and free from dirt, oil or grease before application. Ensure that the substrate is levelled for undulations and having less absorption.
- All surface cracks up to 5 mm should be filled with MYMIX “RITECARE ACF” before priming.
- Cracks more than 5 mm and all separation gaps should be filled with MYMIX “SBR Latex” modified mortar. Bigger cracks, damaged portions and hollow areas must be repaired with polymer modified screed.
- Dampen the surface before application, remove excess water before application.
- The proper preparation of the surface will make the application easier and quicker ensuring a better result.

Application

- Mix well material before use.
- For primer use MYMIX “AQUAFLEX[®] PRIME” directly without any dilution by brush, roller or spray gun.
- Apply MYMIX “AQUAFLEX[®] AWP 350” after adequate curing of primer 2-3 Hrs.
- MYMIX “AQUAFLEX[®] AWP 350” dilute with soft water, 20% by weight for 1st coat and 10% by weight for 2nd coat advantageous and apply with a brush or roller evenly on the surface at a time interval of 5-6 hours.
- After completion allow to dry for adequate time period that may vary as per climate condition 12-24 hours.

❖ Notes on Application / Limitations

- Dilution to be made with clean and low hardness water only.
- Do not apply when ambient temperature is below 10°C or above 45°C.
- Do not apply in direct sunlight and during rainfall.
- Adhesion property may get affected over poor-quality putty and very smooth surfaces.

❖ Technical Data

Parameters	Standard	Measurement Unit	Results
Colour	Visual		White / Teracotta / Grey
Solid Content	ASTM D 2369	%	59.0 - 61.0
Specific Gravity	ASTM D 792	g/cc	1.25 - 1.35
PH	NA	Value	8.00 - 9.50
Hardness (Shore A)	ASTM D 2240: 2002	Shore A	55.0 - 70.0
Tensile Strength	ASTM D 412: 2002	Mpa	>3.0
Elongation at Break	ASTM D 412: 2002	%	>350
Water Resistance	ASTM D 6083	Free form defects	Free form defects
Alkali Resistance	ASTM D 1308	Free form defects	Free form defects
Viscosity Brookfield Sp-7,RPM-10 LVT	ASTM D 2196	cP	40000 - 60000
Adhesion Strength	ASTM D 4541:2002	Mpa	>2.7
UV Resistant - Accelerated	ASTM G 154 :2000	No thermal degradation	Passes
Water Vapour Transmission	ASTM E 96 : 2000	g / hr-m ²	0.95
Algae & Fungus Resistant	SS 345 : 1998	No algae/fungus growth	Passes
Crack Bridging	ASTM C 836 : 1995	mm	>2.0
Rapid Chloride Permeability	ASTM C 1202 - 97	Very Low	Passes
Water Permeability <small>(Depth of penetration at 5 bar pressure)</small>	BS EN 12390, Part 8 :2000	mm	67
Recoat Time @ 30°C	ASTM D 1640 - 03	Hrs	5 - 8
Puncture Resistance	ASTM E 154	lbs.	381
Recommended Thickness (Dry Film)		Micron	450 - 500

❖ Precautions

- Keep out of reach of children
- Wear suitable PPE's when apply
- In case of contact with skin / eyes, wash immediately with plenty of water & seek medical help

Follow us on:



Disclaimer



is a registered trademark of MYMIX BUILDPRO Private Limited.

The information given in this TDS is for general guidance only. Specific instruction for various site conditions can be provided on demand.

The product information & application details given by the company & its agents has been provided in good faith & meant to serve only as a general guideline during usage. Users are advised to carry out tests & take trails to ensure on the suitability of products meeting their requirement prior to full scale usage of our products. Since the correct identification of the problems, qualities of other materials used and on site workmanship are factors beyond our control, there are no expressed or implied guarantee/warranty as to the results obtained. The company does not assume any liability or any consequential damage for unsatisfactory results, arising from the use of our products.